



DYNAMIC REFRACTORIES
REDEFINING EXCELLENCE

GSTIN No. 24AFUPS6913B1Z9

Channel Partner

TRL K ROSAKI REFRACTORIES LTD.

Dealing in REFRACTORIES | CERAMICS | FOUNDRY MATERIALS

PRODUCT DATA	
INSULATION BRICKS	
NAME OF THE PRODUCT	INSULATION BRICKS
PRODUCT QUALITY	COLD-FACE
SERVICE TEMPERATURE (MAX.)	850 DEG. C.
CHEMICAL ANALYSIS	
AL ₂ O ₃ (%) MIN.	22-25
FE ₂ O ₃ (%) MAX.	5
PHYSICAL PROPERTIES	
C.C.S. (Kgs/Cm ²)	70
B.D. (Gms/CC)	-
P.C.E.	-
APPERENT POROSITY (%)	62

NOTE: (ABOVE ARE AVERAGE TEST DATA SUBJECT TO REASONABLE VARIATION)

Plot No. 2302/2, GIDC Phase-4, Vatva, Ahmedabad-382445.

+91 98240 17507 / +91 75678 47733

dynamicrefractories2020@gmail.com,

rajeshsharma.hrr@gmail.com

Bank Name : IndusInd Bank • A/c No. : 259426516169 • Branch : Vatva Industrial Estate • IFSC Code : INDB0001030